The Effects of the Duration of Use on Stiffness of Nickel-Titanium Orthodontic Wires

Ahmad Sheibaninia^{1*}, Parinaz Beikian Ghavidel², Farhang Mahmoudi³

¹Associate Professor, Fellowship of Orthosurgery, Department of Orthodontic, Islamic Azad University, Dental School, Tehran Branch, Tehran, Iran.² Resident, Department of Endodontic, Islamic Azad University, Dental School, Khorasegan Branch, Isfahan, Iran. ³Assistant Professor, Head of Orthodontic Postgraduate Department, Islamic Azad University, Dental School, Tehran Branch, Tehran, Iran.

Abstract

Aim and Background: The wire's stiffness might be changed over the usage time. The present in vivo study was conducted to investigate the effects of duration intervals on the stiffness of Nickel-Titanium (NiTi) orthodontic wires with different cross-sections to identify the appropriate size of wires. **Materials and Method:** The present clinical trial study was conducted on patients who were admitted to the Orthodontics Department of Tehran Dental Branch, Islamic Azad University. Totally, 90 samples of NiTi orthodontic wires, 30 samples with different sizes of 0.014, 0.016, and 0.018 inches were purchased. The measurement of the stiffness had been conducted before, after one month, and after two months of the treatment with 10 samples. The samples were taken to Razi Institute to evaluate archwires' stiffness, using a three-point bending test by Instron tester. Statistical analysis was conducted between and within-group differences using one-way ANOVA. **Results:** The stiffness of the 0.014, 0.016, and 0.018 inch-NiTi wires was insignificantly reduced from 64.0 ± 0.8 , 78.0 ± 1.0 , and 78.0 ± 3.0 N/mm2 before being applied to the mouth to 63.0 ± 3.0 , 77.0 ± 3.0 , and 79.0 ± 4.0 N/mm2 after one month and 62.0 ± 2.0 , 76.0 ± 3.0 , and 78.0 ± 3.0 N/mm2 after two months of being used, respectively (P=0.8, P=0.8, and P=0.06, respectively). **Conclusion:** The stiffness of different cross-sections of NiTi wires did not show any significant changes during the 3 mentioned intervals.

Keywords: Stiffness, NiTi, Orthodontic wire, duration of use

INTRODUCTION

Successful orthodontic therapy depends on not only the manual skills and knowledge of treatment steps but also the knowledge and choice of materials used. One of the major components of fixed orthodontic therapy is the choice of wires ^[1]. One of the concerns of using orthodontic wires is its usage duration. Wires with different alloys including Nickel-Titanium (NiTi), stainless steel (SS), Cobalt-Chromium, and Beta-Titanium are commonly used in dentistry^[2]. The NiTi alloy was first used by Buehler et al. in 1963 for space programs^[3]. There is a wide range of biomedical applications of nickel-titanium due to its Shape Memory Effect (SMA) such as in the field of orthodontics and dentistry like in wires, distractors, palatal arches, endodontic files, etc. ^[4]. Since their introduction to orthodontics in 1971, NiTi wires have been remained popular due to their desirable properties, shape memory alloy (SMA), biocompatibility, environmental stability, stiffness, and elasticity. They are currently and mostly used during the first phase of orthodontic treatment ^[3]; although, this metal is subjected to different types of variations due to high masticatory forces in the mouth and may lose its strength and stiffness ^[5]. Indeed, orthodontic wires are exposed to saliva, water, and various beverages for a long time and have the potential to decrease the strength of fiber-reinforced composites [6, 7].

As we know, nickel-titanium wires have been widely used in orthodontic practice ^[8]. Their desirable mechanical properties and high costs force many clinicians to reuse NiTi wires after sterilization if contaminated ^[9]. In one study, the clinical recycling and cold sterilization of NiTi wires affected their bending abilities and surface properties. Similar changes are inevitable in the mechanical properties of NiTi wires regularly used in clinics and exposed to dry heat sterilization ^[10]. Oral environment corrosion is another major issue with

Address for correspondence: Ahmad Sheibani Nia, Associate Professor, Fellowship of Orthosurgery, Department of Orthodontic, Islamic Azad University, Dental School, Tehran Branch, Tehran, Iran. E-mail: asheibaninia @ yahoo.com

This is an open-access article distributed under the terms of the Creative Commons Attribution-NonCommercial-ShareAlike 3.0 License, which allows others to remix, tweak, and build upon the work noncommercially, as long as the author is credited and the new creations are licensed under the identical terms.

How to cite this article: Sheibaninia, A., Beikian Ghavidel, P., Mahmoudi, F. The Effects of the Duration of Use on Stiffness of Nickel-Titanium Orthodontic Wires. Arch Pharma Pract 2018;9(4):11-4. orthodontic alloys due to the fact that the release of certain amounts of ions can have adverse health effects for patients and causes further friction of the wires ^[11]. However, the results of recent studies suggest that, at least, in the case of stable *in vitro* cultures, Titanium-Niobium (TiNb) SMAs are less toxic than NiTi SMAs. Overall, TiNb SMAs might be a promising solution for specific biomedical applications of NiTi ^[12].

Although most studies on the stiffness of NiTi orthodontic wires have been performed *in vivo*, no similar studies have yet been conducted in Iran ^[13]. Orthodontic wires are required to generate light and continuous biomechanical forces, communicated via brackets, resulting in tooth movement ^[14]. Given the well-known complications of stiff wires and in the light of an *in vitro* study of orthodontic wire stiffness, the present *in vivo* study was conducted to examine the mechanical and dynamic properties of NiTi wires. To improve their efficiency; the findings of the study can be an answer to both theoretical and applied questions and can facilitate the use of such wires at longer intervals of time so that orthodontic treatments can cost less, the patients' health can be promoted, and the knowledge on the subject can be improved.

MATERIALS AND METHOD:

The present clinical trial study was conducted on patients who were admitted to the Orthodontics Department of Tehran Dental Branch, Islamic Azad University. Wires with different cross-sections, made in the USA by American Orthodontic Company were purchased from a local market. Totally 90 samples, 30 samples with different sizes of 0.014, 0.016, and 0.018 inches, used in the clinic, were prepared and placed in the patients' mouth. The samples' stiffness was measured using an Instron tester at three times. The initial stiffness of the mentioned 30 samples was determined (before treatment) in the Research Center laboratory of Karaj Metallurgy, and the data were recorded in Data Form 1. The second measurement of stiffness was performed after the first interval of the treatment by removing those 30 wires from the patients' mouth during a one-month period. One month later and after the second interval of the treatment, the remaining 30 samples were removed from the patients' mouth and their stiffness was similarly measured. Both data related to the first and second intervals were recorded in Data Form 2. Between and within groups differences were analyzed using the oneway analysis of variance (ANOVA) while the Tukey test was used as Posthoc test. P<0.05 was considered significant.

RESULTS:

The stiffness of the 0.014-inch NiTi wires was insignificantly reduced from $64.0\pm0.8 \text{ N/mm}^2$ before placing in the mouth to $63.0\pm3.0 \text{ N/mm}^2$ after one month and $62\pm2 \text{ N/mm}^2$ after two months (P=0.8). A similar insignificant decrease in the stiffness of 0.016 and 0.018-inch NiTi wires was also detected. The stiffness of the 0.016 and 0.018-inch NiTi wires insignificantly reduced from 78.0 ± 1.0 and $80.0\pm0.7 \text{ N/mm}^2$ at the initial stage before its placement in the mouth to

77.0 \pm 3.0 and 79.0 \pm 4.0 N/mm² after one month and 76.0 \pm 3.0 and 78.0 \pm 3.0 N/mm² after two months of use, respectively (P=0.8 and P=0.6). In all three periods, the stiffness of 0.018-inch NiTi wire was higher than the other groups. Moreover, the stiffness of 0.016-inch NiTi wire was higher than 0.014-inch NiTi wire in all three periods of measurement (Table 1).

Table 1: Comparison of stiffness level based on
different cross-sections and times of measurement
(N/mm ²)

Intervals Diameters	Before Treatment	After 1 Month	After 2 Months	P Value
0.014	64±0.8	$63\ \pm 3$	62±2	P<0.8
0.016	78±1	77±3	76±3	P<0.8
0.018	80±0.7	4±79	78±3	P<0.6

DISCUSSION

In the present study, the effect of the use duration on the stiffness of NiTi wires with different cross-sections was evaluated. It was found that the stiffness of all wires with different cross-sections decreased over 2 months but the amount of these declines was not statistically significant. The highest stiffness yielded by the NiTi alloy was related to the 0.018-inch wire before placing in the mouth and the lowest was related to the 0.014-inch wire within a two-month period of use.

The strength, stiffness, and range of actions in a wire are important properties to carry out a specific function at different stages of treatment ^[15]. In addition, high springback, good formability, and low friction are desirable mechanical properties ^[16, 17]. Furthermore, the cross-section of the wire is an important factor, which affects the stiffness. It has been reported that the rectangular wire with larger dimensions had greater stiffness compared to the round wires ^[18]. Similar to our findings, it has been reported that the stiffness of 0.018-wires was more than 0.016-wires, and 0.016-wires were stiffer than 0.014-inch NiTi wires ^[18]. It seems that a long duration of use, high contact with different pH, and the oral cavity environment can be stressful conditions for orthodontic archwires. It has been reported that stress-induced Martensite formation with stress hysteresis, significantly reduced the elasticity and stiffness of NiTi wires ^[19]. In addition, Garrec and Jordan reported that the value of stiffness varied with different sizes of NiTi wires ^[20]. Based on our knowledge in the literature, no similar study exists with a focus on the effects of duration of use and stiffness of NiTi wires.

In 2008, Basafa and his colleagues evaluated the changes of load-deflection rate in 80 commercial NiTi mandibular archwires with a cross-section of 0.0014 inches after a single clinical application in three different crowding. Their samples were randomly divided into four groups of control, mild,

moderate, and severe crowding groups. They found that in 1.5 mm bending, stiffness was 177, 34, 68, and 84 N/mm² in control, mild, moderate, and severe crowding groups, respectively ^[21]. The stiffness of 68 N/m² in moderate crowding groups in their study was close to the stiffness of 64 ± 0.8 N/mm² observed in the 0.014-inch NiTi wire before placement in the mouth in our study. The difference in the results obtained from the two studies can be attributed to different mandibular crowdings and different manufacturers, while the present study only examined maxillary archwires. The distinguishing points and strength in our study include the use of different cross-sections of NiTi wire and different time intervals.

Shen and coworkers in 2013 evaluated the mechanical properties of the 0.014-inch NiTi wires used in the final treatment phase in simulated oral environments. They reported that in groups with 25°, 19°, and 13° deflection, stiffness increased and then decreased. Therefore, they concluded that the mechanical properties of NiTi wires were associated with time and the amounts of deflection and it could affect the treatment outcomes ^[22].

This study had certain limitations such as high costs of tests and approximately low sample size. Also, we only evaluated one type of wire alloy; although, different results may be achieved by different alloys.

CONCLUSION:

As their name implies, the use of fixed orthodontic appliances relies on their bonding to tooth structures ^[23]. In the current study, no significant reduction was observed in the stiffness of the NiTi wires with different cross-sections from the pre-treatment stage to the first and second months of the treatment during different tests. Future studies are recommended to be conducted on larger samples of NiTi orthodontic wires as well as on Stainless Steel orthodontic wires.

ACKNOWLEDGMENTS

This work was based on the thesis of Parinaz Beikian Ghavidel (Thesis No: 24371) for the DDS degree of Azad University. The authors hereby announced that they have active cooperation in this scientific study and preparation of the present manuscript. The authors confirm that they have no financial involvement with any commercial company or organization with direct financial interest regarding the materials used in this study.

References

- Hepdarcan SS, Yılmaz RB, Nalbantgil D. Which Orthodontic Wire and Working Sequence Should be Preferred for Alignment Phase? A Review. Turkish journal of orthodontics. 2016 Jun;29(2):47-50.
- 2. Graber Jr LW. RLV, Vig KWL. Orthodontics: current principles and techniques; 2011.
- 3. Fontana MG. Corrosion engineering. Tata McGraw-Hill Education; 2005.
- 4. Raotiwala, M. Gautam, R. Kalia, A., Hussain, MS. Evaluation of Material Characteristics of Nano Particle Coated and Uncoated Stainless Steel, Nickel-Titanium and Beta-Titanium Orthodontic

Archwire - an In-vitro Study. Scientific Journal of Research in Dentistry, 2018; 2(1): 4-11.

- Carroll WM, Kelly MJ. Corrosion behavior of nitinol wires in body fluid environments. Journal of Biomedical Materials Research Part A: An Official Journal of The Society for Biomaterials, The Japanese Society for Biomaterials, and The Australian Society for Biomaterials and the Korean Society for Biomaterials. 2003 Dec 15;67(4):1123-30.
- Imaia T, Watarib F, Yamagatac S, Kobayashid M, Nagayamae K, Nakamuraf S. Effects of water immersion on mechanical properties of new esthetic orthodontic wire. American journal of orthodontics and dentofacial orthopedics. 1999 Nov 1;116(5):533-8.
- Chai J, Takahashi Y, Hisama K, Shimizu H. Effect of water storage on the flexural properties of three glass fiber-reinforced composites. International Journal of Prosthodontics. 2005 Jan 1;18(1):28-33.
- Omidkhoda M, Poosti M, Sahebnasagh Z, Zebarjad SM, Sahebnasagh Z. Effects of three different mouthwashes on the surface characteristics of nickel-titanium and Stainless steel archwires in orthodontics. Journal of dental materials and techniques. 2017;6(1):19-26.
- Thompson SA. An overview of nickel-titanium alloys used in dentistry. International endodontic journal. 2000 Jul;33(4):297-310.
- McMahon RE, Ma J, Verkhoturov SV, Munoz-Pinto D, Karaman I, Rubitschek F, Maier HJ, Hahn MS. A comparative study of the cytotoxicity and corrosion resistance of nickel–titanium and titanium–niobium shape memory alloys. Acta biomaterialia. 2012 Jul 1;8(7):2863-70.
- Martin-Camean A, Jos A, Mellado-Garcia P, Iglesias-Linares A, Solano E, Camean AM. In vitro and in vivo evidence of the cytotoxic and genotoxic effects of metal ions released by orthodontic appliances: A review. Environmental toxicology and pharmacology. 2015 Jul 1;40(1):86-113.
- 12. Eliades T, Athanasiou AE. In vivo aging of orthodontic alloys: implications for corrosion potential, nickel release, and biocompatibility. The Angle Orthodontist. 2002 Jun;72(3):222-37.
- 13. Kapila S, Haugen JW, Watanabe LG. Load-deflection characteristics of nickel-titanium alloy wires after clinical recycling and dry heat sterilization. American Journal of Orthodontics and Dentofacial Orthopedics. 1992 Aug 1;102(2):120-6.
- 14. Shenai A. Load Deflection Ratios of Various Initial Ni-Ti Wires. International Journal of Physics and Applications, 2018;10(1):1-12.
- Reddy RK, Katari PK, Bypureddy TT, Anumolu VN, Kartheek Y, Sairam NR. Forces in initial archwires during leveling and aligning: An in-vitro study. Journal of International Society of Preventive & Community Dentistry. 2016 Sep;6(5):410-6. PubMed PMID: 27891306. Pubmed Central PMCID: Pmc5109854. Epub 2016/11/29. eng.
- Burstone CJ, Goldberg AJ. Beta titanium: a new orthodontic alloy. American journal of orthodontics. 1980 Feb 1;77(2):121-32. PubMed PMID: 6928342. Epub 1980/02/01. eng.
- Kapila S, Sachdeva R. Mechanical properties and clinical applications of orthodontic wires. American Journal of Orthodontics and Dentofacial Orthopedics. 1989 Aug 1;96(2):100-9. PubMed PMID: 2667330. Epub 1989/08/01. eng.
- Chang JH, Berzins DW, Pruszynski JE, Ballard RW. The effect of water storage on the bending properties of esthetic, fiber-reinforced composite orthodontic archwires. The Angle Orthodontist. 2013 Oct 29;84(3):417-23. PubMed PMID: 24168402. Epub 2013/10/31. eng.
- Liaw YC, Su YY, Lai YL, Lee SY. Stiffness and frictional resistance of a superelastic nickel-titanium orthodontic wire with low-stress hysteresis. American Journal of Orthodontics and Dentofacial Orthopedics. 2007 May 1;131(5):578-e12. PubMed PMID: 17482074. Epub 2007/05/08. eng.
- Garrec P, Jordan L. Stiffness in bending of a superelastic Ni-Ti orthodontic wire as a function of cross-sectional dimension. The Angle Orthodontist. 2004 Oct;74(5):691-6. PubMed PMID: 15529506. Epub 2004/11/09. eng.
- Basafa M, Zebarjad S, Narimani M. Evaluation of load-deflection rate changes of nickel-titanium wire after single clinical application in three different crowdings. Journal of Mashhad Dental School. 2008;32(1):1-0.
- 22. Shen X, Sun XH, Tian H, Zhang CB, Yan K, Guo YL. Mechanical properties of nickel-titanium archwire used in the final treatment phase of Tip-Edge Plus technique: an in vitro study. Chinese medical

journal. 2013 Jan;126(1):135-9. PubMed PMID: 23286492. Epub 2013/01/05. eng.

 Mousavi SM, Ghorani PS, Chitsazi S. Effect of Alginate Impression Taking on Shear Bond Strength of Orthodontic Brackets. Annals of Dental Specialty Vol. 2018 Apr 1;6(2):128.